

H 66430 Büsscher PeriSeal-Tape 200

Product	Adhesive tape made of SBS-modified bitumen with composite reinforcement System-specific bitumen matrix with silicate surface coating for backflow-proof blindside waterproofing	
Top side Bottom side	Silicate coating Full adhesive (peel-off-foil)	
Intended use	 Covering and repairing of Büsscher PeriSeal Concrete Bond System (CBS) for Blindside Waterproofing, according to manfacturer's method statement 	
Application	Self-adhesive method with thermal activation	
Packaging	2 rolls of 10 m = 20 m per box 30 boxes of 20 m = 600 m per pallet	

Characteristics	Testing method	Unit	Result	
Length	EN 1848-1	m	10,0	
Width	EN 1848-1	mm	200	
Thickness	EN 1849-1	mm	3,0 (±0,2)	
Watertightness	EN 1928	kPa	100	
Reaction to fire test	EN 13501-1	Class	E	
Flexibility at low temperatures	EN 1109	°C	-20	
Flow resistance at elevated temperature	EN 1110	°C	100	
The declared data are indices based on the statistical quality control and refer to the date of production. Consider state of the art, standards, legal provisions and quidelines for the				

The declared data are indices based on the statistical quality control and refer to the date of production. Consider state of the art, standards, legal provisions and guidelines for the suitability of the mentioned field of application and application method. All specifications are without obligation. The user must assess the suitability of the product for the particular purpose and ensure the user's access to the current version of the product data sheet.

Subject to alteration without notice.

Storage conditions: The products have to be stored in original packaging, being protected from direct sun light, UV-beams and extreme conditions like heat, frost, moisture, etc. During cold season store the products in a frost-free area (+5°C) for 12 hours before application.

Development, Production and Sales of our products according to ISO 9001.