

H 67241

# Glasvlies GV 120 - A2 (U 120 F)

<b>Product</b>	Glass-fibre
<b>Intended use</b>	Separation and fire protection layer below synthetic roofing sheets
<b>Application</b>	loose laid, side and end laps overlapped

## Packaging

**Attention** The storage period of original packed rolls should not exceed 14 months from production date.

Characteristics	Testing method	Unit	Result
Width		m	2,0 (±2 mm)
Length		m	100 (±0,3 %)
Mass per unit area		g/m <sup>2</sup>	120 (-10,5/ +8,5)
Reaction to fire test	DIN 4102	Class	A2
Fibre diameter		µm	13
Tensile force long.		N/50 mm	245 (-55)
Tensile force trans.		N/50 mm	175 (-40)

The declared data are indices based on the statistical quality control and refer to the date of production. Consider state of the art, standards, legal provisions and guidelines for the suitability of the mentioned field of application and application method. All specifications are without obligation. The user must assess the suitability of the product for the particular purpose and ensure the user's access to the current version of the product data sheet.

**Subject to alteration without notice.**

Storage conditions: The products have to be stored in original packaging, being protected from direct sun light, UV-beams and extreme conditions like heat, frost, moisture, etc. During cold season store the products in a frost-free area (+5°C) for 12 hours before application.

**Development, Production and Sales of our products according to ISO 9001.**